

Polymeric Membranes 1,8"x12"

Model	TYPE	Polymer	CUT-OFF MWCO	Feed Spacer (mm)	Memb. Area (m2)	Temp. Max (°C)	pH RANGE 25°C	Rejection (Test Conditions)	Note
11 163	MF	PVDF	0,20 µm	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 166	MF	PVDF	0,10 µm	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 176	MF	PVDF	0,08 µm	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 177	UF	PVDF	800.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 171	UF	PVDF	500.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 168	UF	PAN	400.000 Da	0,78	0,25	50	2-10		1,18 mm spacer and highT construction available on request
11 167	UF	PES	300.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 178	UF	PVDF	250.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 179	UF	PES	200.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 170	UF	PVDF	200.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 161	UF	PAN	100.000 Da	0,78	0,25	50	2-10		1,18 mm spacer and highT construction available on request
11 174	UF	PES	100.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 180	UF	PVDF	100.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 164	UF	PVDF	70.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 146	UF	PAN	60.000 Da	0,86	0,25	50	2-10		
11 162	UF	PVDF	50.000 Da	0,78	0,37	50	1-11		1,18 mm spacer and highT construction available on request
11 160	UF	PES	50.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 181	UF	PAN	30.000 Da	0,78	0,25	50	2-10		1,18 mm spacer and highT construction available on request
11 182	UF	PES	30.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 183	UF	PVDF	30.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 184	UF	PES	20.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 173	UF	PES	10.000 Da	0,86	0,25	50	1-11		
11 169	UF	PES	5.000 Da	0,86	0,25	50	1-11		
11 143	UF	Thin film	4.000 Da	0,86	0,25	50	1-11		
11 165	UF	PES	3.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 142	UF	Thin film	2.000 Da	0,86	0,25	50	1-11		
11 159	UF	PES	1.000 Da	0,78	0,25	50	1-11		1,18 mm spacer and highT construction available on request
11 141	UF	Thin film	1.000 Da	0,86	0,25	50	1-11		

Polymeric Membranes 1,8"x12"

Model	TYPE	Polymer	CUT-OFF MWCO	Feed Spacer (mm)	Memb. Area (m2)	Temp. Max (°C)	pH RANGE 25°C	Rejection (Test Conditions)	Note
11 158	NF	PA-TFC	800 Da	0,78	0,31	50	3-10	30,0% (2g/l NaCl) 90,0% (2g/l MgSO4)	1,18 mm spacer and highT construction available on request
11 157	NF	PA-TFC	700 Da	0,78	0,31	50	4-10	10,0% (2g/l NaCl) 50,0% (2g/l MgSO4)	1,18 mm spacer and highT construction available on request
11 156	NF	PA-TFC	300-500 Da	0,78	0,31	50	4-10	20,0% (2g/l NaCl) 98,0% (2g/l MgSO4)	1,18 mm spacer and highT construction available on request
11 140	NF	Thin film	400 Da	0,86	0,37	50	0-11	96,0% (2g/l MgSO4)	Acid resistant
11 139	NF	Thin film	200-300 Da	0,86	0,37	50	2-10	96,0% (2g/l MgSO4)	
11 155	NF	PA-TFC	150-300 Da	0,78	0,31	50	3-10	40,0% (2g/l NaCl) 99,0% (2g/l MgSO4)	1,18 mm spacer and highT construction available on request
11 138	NF	Thin film	150-200 Da	0,86	0,37	50	2-10	98,0% (2g/l MgSO4)	
11 153	NF	PA-TFC	100-250 Da	0,78	0,37	50	3-10	55,0% (2g/l NaCl) 99,5% (2g/l MgSO4)	1,18 mm spacer and highT construction available on request
11 175	RO	PA	150 Da	0,86	0,37	50	1-11	96,0% (2g/l NaCl)	
11 152	RO	PA	100 Da	0,86	0,37	50	1-11	98,0% (2g/l NaCl)	
11 135	RO	PA	100 Da	0,86	0,37	50	1-11	>99% (2g/l NaCl)	

Accessories



Housing 1812 High & Low Pressure



Sanitary Membrane 1812